

**SPECIFICATION FOR THE APPLICATION OF
STARWOOD A. F.1®**

Paintings of (1) _____
in order to upgrade the treated material to reaction to fire Class 1 (CNVVF/
UNI 9796)

The product STARWOOD A. F.1® can be applied by (2) _____

The cycle will be applied as follows:

- A) Careful preparation of the wooden surface and humidity control (approx. 12%). The work surfaces must be free of dust, grease, oil, silicon and other substances that may compromise the perfect adherence of the paint. Existing paint coats must be removed by sandblasting.
- B) Application of three or more coats of product with a consumption of 500 g/m².

Application of the STARWOOD A. F.1® costs € _____ per m² including materials. Labour and the preparation of the support are not included.

The STARWOOD A. F.1® is accompanied by Ministerial Approval issued by the Central Technical Service of the Home Office in Rome. The applicator must issue a declaration that the above protective material has been correctly applied.

1) Indicate the type of wood support to treat (wall, matchboard, false ceiling) and the type of the wood.

2) Indicate the application system used (spray, brush, roller, etc.)

For all information that aren't present in this specification for the application, look at data sheet.